

Product Information**CYROLITE® MD™ L40 polymer****PRODUCT PROFILE**

CYROLITE® MD™ L40 acrylic polymer is an amorphous thermoplastic molding compound based on polymethyl methacrylate (PMMA) for the medical diagnostic industry.

TYPICAL PROPERTIES OF CYROLITE® MD™ ACRYLIC POLYMERS ARE:

- exceptional ultra-violet light transmittance (UVT)
- exceptional optical clarity
- good dimensional stability for controlled fluid flow

SPECIAL PROPERTIES OF CYROLITE® MD™ L40 POLYMER ARE:

- highest melt flow rate
- UV light transmitting
- low heat resistance
- medium levels of lubricant

APPLICATION:

Used for injection molding thin-wall medical devices requiring UV spectroscopy for fluid evaluation.

EXAMPLES:

Medical diagnostic parts including cuvettes, test packs and rotors.

PROCESSING:

CYROLITE® MD™ L40 polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

PACKAGING:

Available in 1500 lb. gaylord boxes; other packaging available on request.

REGULATORY AND COMPLIANCE REQUIREMENTS:

Meets requirements of the United States Pharmacopeia Class VI in colorless (000) only; ISO 10993-1 in colorless (000) only and FDA for food contact for all use conditions up to and including hot filled or pasteurized above 150 degrees F (e.g. Condition 21 CFR 176.170) for all food types except those containing more than 8% alcohol.

Properties:

	Parameter	Unit	ASTM-Standard	CYROLITE® MD™ L40 polymer
Mechanical Properties				Typical Value
Tensile Strength		psi [MPa]	D 638	8800 [60.7]
Tensile Modulus		X10 ⁶ psi [GPa]	D 638	0.47 [3.2]
Tensile Elongation @ Yield		%	D 638	2 - 4
Tensile Elongation @ Break		%	D 638	2 - 4
Flexural Strength		psi [MPa]	D 790	14200 [97.9]
Flexural Modulus		X10 ⁶ psi [GPa]	D 790	0.44 [3.0]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.36 [19]
Rockwell Hardness		M Scale	D 785	84
Thermal Properties				
Vicat Softening Point	264 psi	°F [°C]	D 1525	180 [82]
Deflection Temperature, Annealed	1.8 MPa, 0.250"	°F [°C]	D 648	165 [74]
Coeff. of Linear Therm. Expansion	32 - 312°F	in/ in/°F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 - 100°C	mm/mm/°C	D 696	0.000072
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10 min	D 1238	26.0
Optical Properties				
	d = 3.2 mm			
Light Transmission		%	D 1003	92
UV Transmittance	340 nm	%	D 1003	min. 87.7
Haze		%	D 1003	<1
Yellowness Index			D 1925	<1
Other Properties				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.003 - 0.006
Bulk Density		g/cm ³	D 1895	0.66

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

CYROLITE® MD™ L40

For more information on CYROLITE® MD™ L40, visit www.cyrolite.com or call +1 800 225-0172

Evonik Cyro LLC

Methacrylates
299 Jefferson Road
Parsippany, NJ 07054 USA
Phone +1 800 225-0172
www.cyrolite.com

Technical Support: visit the TechKnowlogy Center at cyro.custhelp.com

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

CYROLITE polymer is registered trademark of Evonik Cyro LLC. Evonik is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Evonik Cyro LLC. All rights reserved.