



TRADITIONALLY
INNOVATIVE

PRODUCT INFORMATION

XT® POLYMER X800RG acrylic-based copolymer compound

Product Profile:

XT® POLYMER X800RG compound is an impact-modified acrylic-based copolymer for molding and extrusion applications.

Typical properties of XT® POLYMER acrylic-based copolymer compounds are:

- outstanding thermoformability
- superior heat distortion temperatures
- excellent bonding and welding capabilities
- good impact strength
- good light transmission
- resistant to EtO, gamma and E-beam sterilization
- resistant to PVC stabilizers

The special properties of XT® POLYMER X800RG compound are:

- high melt flow rate
- good chemical resistance

Application:

Used for food packaging and appliance parts.

Examples:

Paper towel dispensers, soap dispensers, sporting goods, battery cases and musical instrument casings.

Processing:

XT® POLYMER X800RG compound can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

Physical Form / Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Properties:

	Parameter	Unit	Standard	XT® POLYMER X800RG acrylic- based copolymer compound
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	2400
Yield Stress	50 mm/min	MPa	ISO 527	48
Yield Strain	50 mm/min	%	ISO 527	3
Nominal Strain @ Break		%	ISO 527	7
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	93
Charpy Notched Impact Strength	23°C	kJ/m ²	ISO 179/1	11
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	97
Rheological Properties				
Melt Volume Rate, MVR	230°C & 3,8kg	cm ³ /10min	ISO 1133	4,3
Optical Properties				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	87
Haze		%	ASTM D1003	7
Other Properties				
Density		g/cm ³	ISO 1183	1.11

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Roehm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved

Roehm America LLC • 8 Campus Drive • Parsippany NJ 07054 • USA
www.cyrolite.com
www.roehm.com

Ref. No.: MC189 A1142

